









G.BLANCO RELIEVE MATE

| | |
|--------------------------------|----------------------------------|
| FORMATO/ <i>FORMAT</i> | 30x90 |
| ESPESOR/ <i>THICKNESS (mm)</i> | 10,5 |
| PRODUCTO/ <i>PRODUCT</i> | REVESTIMIENTO / <i>WALL TILE</i> |
| TIPO/ <i>KIND</i> | ESMALTADO/ <i>GLAZED</i> |
| GRUPO/ <i>GROUP</i> | BIII - GL |

NORMA APLICABLE EN 14411 ANEXO L
APPLICABLE STANDARD ISO 13006 ANNEX L

| ENSAYOS/ <i>TESTS</i> | | RESULTADOS/ <i>RESULTS</i> | |
|---|--|--|--|
|  | UNE-EN ISO 10545-2 DIMENSIONES Y ASPECTO SUPERFICIAL <i>UNE-EN ISO 10545-2 DIMENSIONS AND SURFACE QUALITY</i> | DIMENSIONES <i>DIMENSIONS</i> | CUMPLE CON LA NORMA <i>COMPLIES WITH THE STANDARD</i> |
|  | UNE-EN ISO 10545-3 ABSORCIÓN DE AGUA <i>UNE-EN ISO 10545-3 WATER ABSORPTION</i> | VALOR MEDIO (%) <i>AVERAGE VALUE (%)</i> | 16% |
|  | UNE-EN ISO 10545-4 RESISTENCIA A LA FLEXIÓN <i>UNE-EN ISO 10545-4 MODULUS OF RUPTURE</i> | FUERZA DE ROTURA <i>BREAKING STRENGTH (N)</i> | 600 - 900 N |
|  | | RESISTENCIA A LA FLEXIÓN <i>MODULUS OF RUPTURE (N/mm²)</i> | 15 - 25 N/mm ² |
|  | UNE-EN ISO 10545-9 RESISTENCIA AL CHOQUE TÉRMICO <i>UNE-EN ISO 10545-9 THERMAL RESISTANCE</i> | RESULTADO <i>RESULT</i> | RESISTE <i>RESISTS</i> |
|  | UNE-EN-ISO 10545-11 RESISTENCIA AL CUARTEO <i>UNE-EN-ISO 10545-11 CRAZING RESISTANCE</i> | RESULTADO <i>RESULT</i> | RESISTE <i>RESISTS</i> |
|  | UNE-EN ISO 10545-13 RESISTENCIA QUÍMICA <i>UNE-EN ISO 10545-13 CHEMICAL RESISTANCE</i> | CLORURO AMÓNICO <i>AMMONIUM CHLORIDE 100 g/l</i> | A |
| | | HIPOCLORITO SÓDICO <i>SODIUM HYPOCHLORITE 20 mg/l</i> | A |
| | | ÁCIDO CLORHÍDRICO <i>HYDROCHLORIC ACID 3%</i> | CUMPLE CON LA NORMA <i>COMPLIES WITH THE STANDARD</i> |
| | | ÁCIDO CÍTRICO <i>CITRIC ACID 100 g/l</i> | |
| | | HIDRÓXIDO POTÁSICO <i>POTASSIUM HYDROXYDE 30 g/l</i> | |
| | | ÓXIDO VERDE EN ACEITE LIGERO <i>GREEN AGENT IN LIGHT OIL</i> | 5 |
|  | UNE-EN ISO 10545-14 RESISTENCIA A LAS MANCHAS <i>UNE-EN ISO 10545-14 STAIN RESISTANCE</i> | SOLUCIÓN ALCOHÓLICA DE YODO <i>IODINE SOLUTION IN ALCOHOL</i> | 5 |
| | | ACEITE DE OLIVA <i>OLIVE OIL</i> | 5 |

OBSERVACIONES:

VºBº LABORATORIO:

