








**G.ELBERT MARFIL**

FORMATO/ <i>FORMAT</i>	30X90
ESPESOR/ <i>THICKNESS (mm)</i>	10,5
PRODUCTO/ <i>PRODUCT</i>	REVESTIMIENTO / <i>WALL TILE</i>
TIPO/ <i>KIND</i>	ESMALTADO/ <i>GLAZED</i>
GRUPO/ <i>GROUP</i>	BIII - GL



NORMA APLICABLE EN 14411 ANEXO L  
APPLICABLE STANDARD ISO 13006 ANNEX L

ENSAYOS/ <i>TESTS</i>		RESULTADOS/ <i>RESULTS</i>	
	UNE-EN ISO 10545-2 DIMENSIONES Y ASPECTO SUPERFICIAL	DIMENSIONES	CUMPLE CON LA NORMA
	UNE-EN ISO 10545-2 DIMENSIONS AND SURFACE QUALITY	DIMENSIONS	COMPLIES WITH THE STANDARD
	UNE-EN ISO 10545-3 ABSORCIÓN DE AGUA	VALOR MEDIO (%)	16%
	UNE-EN ISO 10545-3 WATER ABSORPTION	AVERAGE VALUE (%)	
	UNE-EN ISO 10545-4 RESISTENCIA A LA FLEXIÓN	FUERZA DE ROTURA	600 - 900 N
	UNE-EN ISO 10545-4 MODULUS OF RUPTURE	BREAKING STRENGTH (N)	
		RESISTENCIA A LA FLEXIÓN	15 - 25 N/mm <sup>2</sup>
	MODULUS OF RUPTURE (N/mm <sup>2</sup> )		
	UNE-EN ISO 10545-9 RESISTENCIA AL CHOQUE TÉRMICO	RESULTADO	RESISTE
	UNE-EN ISO 10545-9 THERMAL RESISTANCE	RESULT	RESISTS
	UNE-EN-ISO 10545-11 RESISTENCIA AL CUARTEO	RESULTADO	RESISTE
	UNE-EN-ISO 10545-11 CRAZING RESISTANCE	RESULT	RESISTS
	UNE-EN ISO 10545-13 RESISTENCIA QUÍMICA	CLORURO AMÓNICO	A
		AMMONIUM CHLORIDE 100 g/l	
		HIPOCLORITO SÓDICO	A
		SODIUM HYPOCHLORITE 20 mg/l	
		ÁCIDO CLORHÍDRICO	CUMPLE CON LA NORMA
		HYDROCHLORIC ACID 3%	COMPLIES WITH THE STANDARD
		ÁCIDO CÍTRICO	
CITRIC ACID 100 g/l			
UNE-EN ISO 10545-13 CHEMICAL RESISTANCE	HIDRÓXIDO POTÁSICO		
	POTASSIUM HYDROXYDE 30 g/l		
	ÓXIDO VERDE EN ACEITE LIGERO	5	
	UNE-EN ISO 10545-14 RESISTENCIA A LAS MANCHAS	GREEN AGENT IN LIGHT OIL	
		SOLUCIÓN ALCOHÓLICA DE YODO	5
		IODINE SOLUTION IN ALCOHOL	
		ACEITE DE OLIVA	5
		OLIVE OIL	

OBSERVACIONES:

VºBº LABORATORIO:

